


DFW / 3682



PTO/SB/21 (09-04)
 Approved for use through 07/31/2006. OMB 0651-0031
 U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
 Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

TRANSMITTAL FORM <i>(to be used for all correspondence after initial filing)</i>	Application Number	10/521,072-Conf. #4421
	Filing Date	June 20, 2003
	First Named Inventor	Charan P. Johal
	Art Unit	3682
	Examiner Name	Not Yet Assigned
Total Number of Pages in This Submission	Attorney Docket Number	60680-2005

ENCLOSURES (Check all that apply)		
<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached <input type="checkbox"/> Amendment/Reply <input type="checkbox"/> After Final <input type="checkbox"/> Affidavits/declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input checked="" type="checkbox"/> Certified Copy of Priority Document(s) <input type="checkbox"/> Reply to Missing Parts/Incomplete Application <input type="checkbox"/> Reply to Missing Parts under 37 CFR 1.52 or 1.53	<input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> Petition <input type="checkbox"/> Petition to Convert to a Provisional Application <input type="checkbox"/> Power of Attorney, Revocation Change of Correspondence Address <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Request for Refund <input type="checkbox"/> CD, Number of CD(s) _____ <input type="checkbox"/> Landscape Table on CD	<input type="checkbox"/> After Allowance Communication to TC <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to TC (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Other Enclosure(s) (please identify below): Return Receipt Postcard
<div style="border: 1px solid black; padding: 2px; display: inline-block;">Remarks</div>		

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT			
Firm Name	RADER, FISHMAN & GRAUER PLLC		
Signature			
Printed name	Michael B. Stewart		
Date	September 28, 2005	Reg. No.	36,018

Transmittal	
I hereby certify that this correspondence is being deposited with the U.S. Postal Service with sufficient postage as First Class Mail, in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450, on the date shown below.	
Dated: September 28, 2005	Signature: (Alisa M. Haggemo)

Best Available Copy

THIS PAGE BLANK (uspto)



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

**CERTIFIED COPY OF
PRIORITY DOCUMENT**


Signed

Stephen Hordley

Dated

6 January 2005

THIS PAGE BLANK (USPTO)



Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

13 JUL 2002

The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference
P021570GB

2. Patent application number
(The Patent Office will fill in this part)

0216331.9

16JUL02 E733312-1 D02973
P01/7700 0.00-0216331.9

3. Full name, address and postcode of the or of each applicant (underline all surnames)

DANA Corporation
4500 Dorr Street
P O Box 1000
Toledo, Ohio 43615
USA

Patents ADP number (if you know it)

51649002

If the applicant is a corporate body, give the country/state of its incorporation

Commonwealth of Virginia, USA

4. Title of the invention

Bearings

5. Name of your agent (if you have one)

Harrison Goddard Foote

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Orlando House
11c Compstall Road
Marple Bridge
Stockport SK6 5HH
United Kingdom

Patents ADP number (if you know it)

14571002

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Yes

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

15

Claim(s)

2

Abstract

1

Drawing(s)

8

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

1

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

Cover letter, fee sheet and cheque

11.

I/We request the grant of a patent on the basis of this application.

Signature *Hamir Goddard Foster* Date

12 July 2002

12. Name and daytime telephone number of person to contact in the United Kingdom

David Goddard 0161 427 7005

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645-500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

DUPLICATE

P021570GB

BEARINGS

5 The present invention relates to plain journal bearings, particularly though not exclusively, for internal combustion engines and to so-called overlay coatings deposited upon the running sliding surface of such bearings.

10

Overlay coatings on plain journal bearings are well known. Such coatings are used to improve the running characteristics of plain bearings. Generally, overlay coatings are relatively soft metal alloys having a
15 hardness in the region of about 15Hv; are frequently based on alloys of lead; and, are deposited on another harder bearing alloy at a thickness in the range from about 10 to 30µm. Overlay alloys of the type under consideration are usually applied by electro-deposition
20 from aqueous plating solutions.

The bearings on which the overlays are deposited are of generally cylindrical or, more commonly, semi-cylindrical form as half-bearing shells which support the crankshaft
25 journals of internal combustion engines, for example. Such bearings generally comprise a layer of a strong backing material such as steel, for example, on which is a layer of a bearing material frequently chosen from alloys of aluminium or copper. The method of attaching
30 the layer of bearing alloy to the strong backing may be any that is suitable and may include techniques such as pressure welding of sheets of bearing alloy to the backing; the casting of molten alloy onto the backing; or, the sintering of powders of alloy to the backing, for

example, these methods not being exhaustive. The overlay alloy coating is deposited on the surface of the harder bearing alloy and endows the finished bearing so formed with properties which include conformability and the ability to embed dirt particles and so prevent scoring of a shaft journal by particles of debris carried in the lubricating oil. Although overlay alloys in their bulk form are relatively weak alloys, they have the ability when applied as a thin layer to another, harder bearing alloy to increase the fatigue strength of a bearing embodying that harder and intrinsically stronger bearing alloy. This is effected due to the conformability of the overlay alloy by being able to deform slightly to accommodate slight mis-alignments, especially in new engines during the "running in" phase, and so spread the load more evenly across the bearing surface area.

As noted above, many conventional overlay alloys are based on alloys of lead. Lead is a toxic metal which will eventually be phased out of use by governmental legislation throughout the world. In order to make the lead overlay layer less prone to corrosion in hot engine oils about 10 weight% of tin is frequently added or, alternatively, 7 to 10 wt% of indium. Indium, however, is relatively very expensive compared with tin and tends to be used for more expensive, higher performance vehicles. However, when tin is used in the overlay alloy and is deposited upon a harder bearing alloy such as copper-lead, for example, a problem exists in that the tin under engine operating conditions tends to diffuse out of the overlay into the lead of the underlying bearing alloy, as does indium. This is solved by coating the surface of the underlying, harder bearing alloy with a thin diffusion barrier of about 1-3 μ m of a metal such as nickel.

However, this is not entirely satisfactory as diffusion still occurs and the overlay still becomes depleted in tin due to the formation of non-equilibrium intermetallic compounds such as Ni_3Sn or Ni_3Sn_2 which are not good bearing materials in the situation where the shaft journal wears through the overlay to the underlying interface comprising these intermetallic compounds.

With the ever increasing demands placed on bearings by engines having higher specific outputs and operating at higher engine revolutions, there has been a demand for these relatively soft overlay alloys to have improved wear resistance whilst at least maintaining existing levels of fatigue, cavitation and corrosion resistance. This demand has resulted in the development of so-called lead-tin-copper overlay alloys an example of which is Pb-10Sn-2Cu .

Thus, it is an object of the present invention to provide an overlay layer which is not toxic and a further object to provide an overlay which does not form undesirable compounds at an interface with an underlying, harder bearing material. A yet further object is to provide an overlay having improved performance over known lead-based overlay alloys.

According to a first aspect of the present invention there is provided a plain bearing having an overlay material layer at a sliding surface of the plain bearing, the plain bearing comprising a layer of a strong backing material, a layer of a first bearing alloy bonded to the strong backing material and a layer of a second bearing alloy comprising said overlay material bonded to said first bearing alloy layer wherein said second bearing

material comprises tin having included in the matrix thereof an organic levelling agent.

5 The tin overlay layer according to the present invention comprises essentially pure tin in that there are no metallic alloying constituents, other than unavoidable impurities, however, the tin is deposited from a bath containing additions of one or more organic materials which have the effect of so-called "levelling" on the
10 electro-deposited tin layer.

Organic materials which have been tested in bearings of the present invention embodying tin overlays include nonylphenolpolyglycolether and pyrocatechol. The content
15 of the organic material in the plating bath has an influence on the degree of levelling achieved in the deposited tin layer, the degree of levelling being reflected in the surface roughness of the tin layer.

20 At low levels of organic levelling agent, too low for the full benefit of the present invention to be felt, the surface appearance of the bearing surface is one of a general crystalline appearance having pools of smooth material distributed over the surface. At a content of
25 organic levelling agent where the whole surface is smooth, this is the desirable minimum content.

It is believed that the organic levelling agent is incorporated in the matrix of the deposited tin layer as
30 polymer chains occluded in the matrix structure such as in the form of an organo-metallic tin compound, for example. The polymer chains appear to impart a preferred orientation to the tin atoms during deposition which has been found to give improved slip properties. Improved
35 slip properties have been evidenced by lower coefficients

of friction in the tin layer compared with ordinary tin deposits without the levelling additions. The surface of the tin overlay of the bearing of the present invention is very smooth giving a lower degree of friction against a co-operating shaft journal which in turn gives improved compatibility between bearing surface and shaft journal resulting in lower wear rates.

The organic constituent of the tin overlay produces an increased hardness in the range from about 20 to 30Hv. Pure tin with no organic levelling agent, depending upon its condition, has a hardness of about 8-12Hv. The hardness of the tin overlay can be changed depending upon the content of the organic levelling agent in the plating bath; the lower the content, the lower the corresponding hardness. The reverse is also true in that as the content of levelling agent increases, so also does the hardness. However, it is possible to have too high a content of organic levelling agent such that the hardness is too high and high internal stresses are produced in the deposit which can lead to cracking of the tin deposit. It is intended that the overlay of the bearing of the present invention operates in a similar manner to conventional overlays in that the overlay layer is sufficiently soft to permit particles of dirt circulating in the lubricating oil to become embedded in the overlay so as to prevent such dirt particles from scoring the shaft journal. Whilst the tin overlay of the present invention is harder than pure tin by a factor of X2 to X3 it is still sufficiently soft to provide the required characteristic of dirt embeddability thus, the preferred hardness range is 20 to 30Hv.

The bearing of the present invention may preferably have an interlayer between the surface of the first bearing

material and the tin overlay to act as a diffusion barrier therebetween. The metal layer may be of a thickness lying in the range from about 0.1 to about 3 μ m with a thickness of 1 to 2 μ m being commonly used, however, the actual thickness is of comparatively little importance in terms of bearing performance. The metal may be selected from the non-exhaustive group including nickel, cobalt, copper, silver, iron and alloys of these metals, for example. It has been found that under engine operating conditions the tin overlay reacts with the interlayer over time to form the stable equilibrium intermetallic compound, Ni₃Sn₄, due to the presence of effectively an excess of tin. As noted above, prior art lead-10tin overlays tended to form the unstable, non-equilibrium Ni₃Sn or Ni₃Sn₂ compounds which are poor bearing materials and have inferior compatibility with a shaft journal and have been blamed in the past for causing seizure when the overlay has worn through to the interlayer. Ni₃Sn₄ on the other hand is a very good bearing material and thus, the overlay of the present invention in addition to having superior resistance to wear and cavitation erosion is also less prone to seizure when the overlay is nearing the end of its life. Thus, this unforeseen effect of generating a good bearing material at the interface is seen as a significant advantage of the bearing of the present invention.

As with known overlay layers, the thickness of the overlay of the bearing of the present invention may lie in the range from about 10 to 30 μ m with 13 to 18 μ m being preferred.

The deposition conditions for tin overlays according to the present invention may be varied to produce a range of

microstructures. For example, analysis of the tin overlay layer by SEM has revealed no discernible grain size; even at magnifications of X5000 and X10000 no grains can be resolved. However, coatings having grain sizes of up to 3µm may be produced. It is preferred, however, that a smaller grain size is produced as these provide improved bearing properties.

According to a second aspect of the present invention, there is provided a method for the deposition of an overlay layer onto the surface of a plain bearing, the bearing comprising a strong backing material having a layer of a first bearing material thereon, said overlay being deposited upon the surface of said first bearing material, the method comprising the steps of: providing a bearing having a surface on which to deposit said overlay; immersing said bearing in a plating solution having a supply of tin ions and an organic levelling agent in said solution; making said bearing cathodic with respect to an anode in said solution; and depositing an overlay of tin, apart from unavoidable impurities, said tin overlay also having said organic levelling agent included in a matrix thereof.

It is preferred to deposit the tin overlay of the bearing of the present invention by using a so-called "slot jig" wherein the bearing is held with its joint faces against a back face of the slot jig with the bore of the bearing facing the slot, the bearing axis and slot being generally parallel to each other. The plating solution, in which the bearing and slot jig are immersed, is also then sparged through the slot towards the bearing bore. In this way it has been found that relatively high current densities of 2 to 3 A/dm² may be employed

- compared with less than 1 A/dm² where the bearing is merely immersed in the plating solution without sparging thereof. Furthermore, the quality of the deposited tin layer is greatly improved compared with that produced without sparging. The use of high current density permitted by the slot jig and sparging technique also reduces plating time from more than 40 minutes to less than 20 minutes.
- 10 A typical plating solution producing a tin/organic material overlay on a bearing according to the present invention may have a composition as follows:
- | | | |
|----|--------------------------------|-------------|
| | Sn ⁺⁺ | 32-38 g/l |
| 15 | SnSO ₄ | 58-68 g/l |
| | H ₂ SO ₄ | 185-210 g/l |
| | Cu | <50mg/l |
| | Chloride | <20ppm |
- 20 Levelling agent additions of nonylphenolpolyglycolether (10-25%) in a methanol carrier (2.5-10%) in the range from 18 to 70 ml/l to the solution specified above have been tested. At the lower end of the range it was found that the degree of levelling and hardness increase was
- 25 insufficient whilst at the upper end of the range it was found that there was too much inherent stress in the tin deposit and cracking occurred. It was found that concentration in the range from 25 to 55ml/l gave useful increases in overlay performance with little or
- 30 acceptable deterioration of the fundamental requirements of an overlay alloy in terms of conformability and dirt embeddability. The content of pyrocatecol was 2.5-10% and amphoterics tensid 2.5% maximum.

It has been found that the leveller content has a substantially directly proportional effect on hardness of the tin deposit. However, a limit of leveller content is reached after which the hardness of the tin deposit remains constant and then actually begins to fall after further increasing the leveller content. Similarly, the leveller content also has a directly proportional effect on surface roughness once the effect of the initial substrate roughness and greatly increased surface roughness of the initial leveller-free tin deposit have been overcome.

In order that the present invention may be more fully understood, examples will now be described by way of illustration only with reference to the accompanying figures, of which:

Figure 1 shows a cross section through a part of a schematic bearing according to the present invention showing the constituent layers;

Figure 2 shows a top view of a schematic arrangement of a plating jig having a bearing being plated with a tin/organic material according to the method of the present invention;

Figure 3 shows a histogram of mean thickness loss of overlay vs main journal number in an engine test comparing bearings according to the present invention and bearings plated with known Pb/In overlays;

Figure 4 shows a histogram of weight loss vs main journal number of overlays of bearings according to the present invention and known Pb/In plated bearings in a 3000hour engine test;

Figure 5 shows a histogram of volume loss of overlays of bearings according to the present invention and known Pb/In and Pb/Sn/Cu overlays in a hot oil corrosion test;

5

Figure 6 shows a histogram of fatigue strength of bearings according to the present invention having a tin/organic material overlay and known Pb/In and Pb/Sn/Cu overlays;

10

Figure 7 shows a histogram of volume loss of overlays of bearings according to the present invention, Pb/Sn/Cu and Pb/In overlays;

15 Figure 8 shows a graph of leveller content vs hardness; and

Figure 9 which shows a graph of leveller content vs surface roughness of the deposit on a substrate.

20

Referring now to Figure 1 which shows a cross section of a small portion of a generalised bearing 10 according to the present invention. The bearing comprises: a strong backing material 12 (only a part of the thickness of which is shown); a layer of a first bearing material 14 bonded to the backing 12; an interlayer 16; and, an overlay layer 18 of tin which includes an organic levelling agent combined in the matrix thereof. The backing layer 12 may be steel, for example, but may be any other suitable material such as bronze for example if corrosion conditions in the application dictated such. The first bearing material layer 14 may be any that is suitable but will generally be chosen from copper-based alloys or aluminium-based alloys. The interlayer 16 is present to form a diffusion barrier to stop rapid

25

30

35

diffusion of the tin from the overlay 18 into the bearing alloy layer 14 in the case of copper-based alloys 14 and to improve the adhesion of the overlay to the bearing alloy in the case of aluminium-based alloys 14. The

5 interlayer will generally be deposited by electro-deposition where the overlay is so deposited and may comprise a layer of nickel or other suitable material as described hereinabove. In use, the bearing 10 will be subject to temperatures up to about 160°C. At

10 temperatures of 90°C and above, the tin from the overlay will react with the interlayer material to form the stable intermetallic compound Ni_3Sn_4 in the case of a nickel interlayer. The rate of formation increases as the temperature rises. The Ni_3Sn_4 layer grows at the expense

15 of the overlay, however, the Ni_3Sn_4 layer is a good bearing material per se with good compatibility with the co-operating shaft journal (not shown) and thus, does not present a possible seizure threat. The thickness of the interlayer 16 generally lies in the range from 1 to 3 μm

20 and the thickness of the overlay 18 generally in the range from 13 to 18 μm .

Figure 2 shows a top plan view of a schematic arrangement

20 of electro-plating apparatus for depositing an overlay 18 on a bearing 10. The apparatus comprises a jig 22

25 having two plates 24, 26 spaced either side of a slot 28. The bearing 10 is held against the plates 24, 26 on its joint faces 30. The jig 22 is immersed in a bath (not shown) of plating solution 32 as is a tin anode 34 of

30 generally cylindrical form. The bearing 10 is made cathodic by a suitable electrical connection (not shown). A sparging tube 36 having holes 38 is situated vertically in the bath in a fixed relationship to the slot 28. Plating solution is pumped through the tube 36 so as to

emerge in jet form, as indicated by the arrows 40, which are directed towards the bore of the bearing 10 through the slot 28. Although not apparent from Figure 2, the jig 22 is elongate as are the anode 34 and sparging tube 36 and there is generally a stack of a plurality of bearings 10 being plated simultaneously.

In the tests results which follow, the overlay was deposited upon the relevant substrate alloy bearing alloy 14 and interlayer 16 from a plating bath having the following composition:

Sn ⁺⁺	32-38 g/l
SnSO ₄	58-68 g/l
H ₂ SO ₄	185-210 g/l
Cu	<50mg/l
Chloride	<20ppm

Levelling agent additions of nonylphenolpolyglycolether (10-25%) in a methanol carrier (2.5-10%) in the range from 32 to 35 ml/l were added to the above aqueous solution.

The interlayer 16 material was in all case nickel.

Figure 3 indicates the results of a 3000 hour test on a diesel truck engine. Main bearings 1 to 4 inclusive were fitted with bearings according to the present invention as described above whilst main bearings 5 to 7 inclusive were fitted with bearings of the same material and construction but having a conventional overlay of Pb-7In. As may be seen from the histogram of Figure 3, the mean overlay thickness loss for bearings of the present

invention was less than 10% that of the conventional overlay.

Figure 4 shows the results of the 3000 hour Volvo engine test of Figure 3 in terms of weight loss. Weight loss of the bearings according to the present invention was significantly less than 100mg each for the four main bearings on journals 1 to 4 whereas the weight loss of the bearings on journals 5 to 7 was around 1000 mg each.

Figure 5 is a histogram showing weight loss of overlays in hot oil (white medicinal oil which is chosen for its particularly corrosive nature) after 1000 hours at 120°C, the loss being measured in mm³. The bearing material on which the overlays were deposited has a composition CuSn10 which was cast onto steel. The overlays were tin as in the present invention, Pb-7In and Pb-10Sn-2Cu. As may be seen from Figure 5, the volume loss of overlays on bearings according to the present invention was about 60% that of Pb-10Sn-2Cu and much less than 10% that of the Pb-7In overlay.

Figure 6 is a histogram showing the fatigue strength of bearings having the overlays specified. The bearings according to the present invention were tested in two forms: one having a thickness of 18µm at the upper end of the preferred thickness range; and, the second having a thickness of 14µm at the lower end of the preferred thickness range. The overlay thicknesses of the prior art Pb-10Sn-2Cu and Pb-7In overlays was 15-16µm. As may be seen from Figure 6 the fatigue strength of the bearings according to the present invention was significantly greater than the prior art bearings.

Further tests carried out where the tin overlay in a thickness in the range from 13 to 18 μ m was deposited on bearing materials 14 of Cu-30Pb-1.5Sn and Cu-10Sn gave fatigue strengths of 90 to 103 MPa.

5

Figure 7 is a histogram showing wear test results showing volume loss of overlay on bearings according to the present invention compared with conventional overlays as described hereinabove. The test conditions were:

- 10 temperature 120°; load 8kg; speed 500 rev/min; duration 10 mins; and a constant flow of 10W oil at 600ml/min. As may be seen from Figure 7 the volume loss of overlays according to the present invention is less than 50% of Pb-10Sn-2Cu and less than 40% that of Pb-7In.

15

- Tests were also carried out on the cavitation resistance of overlays on bearings according to the present invention. In these tests, the weight loss of the tin overlay of the inventive bearing was 9mg whereas the weight loss of a Pb-7In overlay under identical conditions was 37mg.

20

- Figure 8 shows the effect of leveller content on the hardness of the tin deposit. It may be seen that the hardness increases linearly with increasing content of leveller which was the same as that in the previously described example.

25

- Figure 9 shows the effect of leveller content on surface roughness of the tin deposit. At low leveller contents below about 2 ml/l of leveller, the high roughness is a consequence of the substrate surface roughness which was an Ra of 0.44 and the roughening effect of the initial, substantially leveller-free tin deposit. Once the effect

30

of the leveller was such that the surface roughness matched that of the substrate then increasing quantities of leveller were directly proportional to the surface roughness.

5

Thus, relatively low contents of leveller have a strong effect in hardening and smoothing out surface roughness of the tin overlays of the present invention.

10 Thus, it may be seen that the performance of overlays on bearings according to the present invention is greatly superior to the best conventional overlays deposited by electro-deposition. Where the overlay is deposited upon a lead-free bearing material 14, the bearing of the present
15 invention provides a completely lead-free bearing which complies with future legislation relating to the elimination of lead from vehicles.

CLAIMS

1. A plain bearing having an overlay alloy layer at a sliding surface of the plain bearing, the plain bearing comprising a layer of a strong backing material, a layer of a first bearing alloy bonded to the strong backing material and a layer of a second bearing material comprising said overlay material bonded to said first bearing alloy layer wherein said second bearing material comprises tin having included in the matrix thereof an organic levelling agent.
2. A plain bearing according to claim 1 wherein the organic material is selected from at least one of: nonylphenolpolyglycolether and pyrocatechol.
3. A plain bearing according to either claim 1 or claim 2 wherein the hardness of the overlay is in the range from about 20 to 30Hv.
4. A plain bearing according to any one preceding claim further including an interlayer between the surface of the first bearing material and the tin overlay to act as a diffusion barrier therebetween.
5. A plain bearing according to claim 4 wherein the interlayer is selected from the group comprising: nickel, cobalt, copper, silver, iron and alloys thereof.
6. A method for the deposition of an overlay layer onto the surface of a plain bearing, the bearing comprising a strong backing material having a layer of a first bearing material thereon, said overlay being deposited upon the surface of said first bearing material, the method comprising the steps of: providing a bearing having a surface on which to deposit said overlay; immersing said bearing in a plating solution having a supply of tin ions and an

- organic levelling agent in said solution; making said bearing cathodic with respect to an anode in said solution; and depositing an overlay of tin, apart from unavoidable impurities, said tin overlay also having said organic levelling agent included in a matrix thereof.
- 5
7. A method according to claim 6 wherein the overlay is deposited in a slot jig apparatus.
8. A method according to claim 7 wherein the plating solution is sparged through the slot towards the bearing bore.
- 10
9. A method according to either claim 6 or claim 7 wherein a plating current density lies in the range from 2 to 3 A/dm².
- 15
10. A plain bearing having an overlay layer at a sliding surface of the plain bearing substantially as hereinbefore described with reference to the accompanying description and drawings.
11. A method for the deposition of an overlay layer onto the surface of a plain bearing substantially as hereinbefore described with reference to the accompanying description and drawings.
- 20

ABSTRACT

A plain bearing and method for making the plain bearing are described, the plain bearing having an overlay alloy layer at a sliding surface of the plain bearing, the plain bearing comprising a layer of a strong backing material, a layer of a first bearing alloy bonded to the strong backing material and a layer of a second bearing material comprising said overlay material bonded to said first bearing alloy layer wherein said second bearing material comprises tin having included in the matrix thereof an organic levelling agent.




Fig. 1

BEST AVAILABLE COPY





Fig. 2

This Page Blank (uspto)

THIS PAGE BLANK (uspto)

Engine Test Mean Thickness Losses From Both Bearings at Each Journal after 3000 hours



BEST AVAILABLE COPY

Fig: 3

This Page Blank (uspto)
THIS PAGE BLANK (uspto)

Engine Test 3000hr Comparison of wt. Loss between Sn and PbIn main bearings

BEST AVAILABLE COPY




Fig 4

This Page Blank (uspto)
THIS PAGE BLANK (uspto)

Hot Oil Corrosion

Tin on F90 vs.
two standard
lead-based
systems

BEST AVAILABLE COPY




Fig. 5

This Page Blank (uspto)
THIS PAGE BLANK (uspto)

Sapphire fatigue test data




Fig. 6

This Page Blank (uspto)
THIS PAGE BLANK (uspto)

Wear test data




Fig. 7

BEST AVAILABLE COPY

This Page Blank (uspto)
THIS PAGE BLANK (USPTO)

Hardness vs. Additions of Leveller




Fig. 8

This Page Blank (suspto)




Fig. 9.

BEST AVAILABLE COPY

This Page Blank (uspto) :
THIS PAGE BLANK (USPTO)